

TECHNICAL DATA SHEET

QUAKERCLEAN® 624 JBS

DUAL PURPOSE CLEANER AND METAL PRESERVATIVE

QUAKERCLEAN® 624 JBS is a mild alkaline liquid that simultaneously cleans and protects metal surfaces in a single processing step.

Applications

QUAKERCLEAN® 624 JBS is designed for ferrous (steel and cast iron) alloys and non-ferrous (aluminum) alloys.

Customers

- Chrysler
- Ford
- General Motors
- TRW
- Balkor
- Dana
- Koyo

Corporate Approvals

- Caterpillar # 3-9837336
- Chrysler NPM # 12-270-6050
- Ford TOX # 175019
- General Motors HMCS ID 1182432

Health, Safety and Handling

Please consult the Safety Data Sheet (SDS) for information on storage, safe handling and disposal. The conditions or methods of handling, storage, use and disposal of the product are beyond our reasonable control - we assume no liability for any ineffectiveness of the product or any injury or damage, arising out of or in connection with these conditions. This product has a shelf life of 12 months, and it should be stored out of direct sunlight in temperatures between 40°F (4°C) and 100°F (38°C).

Benefits

- Used to clean and protect metal surfaces in one step simplifying operations and keeping inventory costs low. Product will provide 30 days of corrosion protection to the metal surface when not rinsed
- Safe for use on both ferrous and non-ferrous metals. This single product can be used for two applications reducing inventory and costs
- Moderate pH and very worker compatible
- Low foam generation at temperatures up to 150°F which means less product consumption, lower costs and prevents pump cavitation

Properties

PROPERTY	TYPICAL VALUE	UNIT
Appearance	Clear to slightly hazy light yellow	
Pounds per gallon at 60°F	8.64	lbs/gal
Neat pH at 77°F	10.4	
Flash Point via COC	Boils at 100 / 212	°C/°F
Odor	Surfactant	
pH (5% distilled water)	9.9	
Appearance (10% dilution)	Clear, light yellow solution	

Compatibility

To enhance process compatibility, use Quaker Houghton metalworking fluids and corrosion preventives.



QUAKERCLEAN® 624 JBS

DUAL PURPOSE CLEANER AND METAL PRESERVATIVE

Fluid Maintenance

This product can be used in one- or multi-stage spray and immersion systems as defined below.

SPRAY EQUIPMENT

Concentration	3-5% by Volume
Temperature	Ambient to 150°F
Pressure	5-60 psi
Contact Time	Dependent on soil condition of part

IMMERSION EQUIPMENT

Concentration	3-8% by Volume
Temperature	Ambient to 150°F
Contact Time	2 - 10 minutes

Water rinsing is not necessary, as the residual film will provide short-term indoor corrosion protection. An Alkalinity Titration to determine the concentration of this product is available upon request. Please consult with your Quaker Houghton representative.

All reasonable care has been taken to ensure this publication is accurate upon issue. Such information may be affected by changes subsequent to issue. This Technical Data Sheet is to be used solely for this product. Prior to any use, consult the Safety Data Sheet (SDS) for information on hazard risks and product use parameters. All liability and all warranties express or implied are hereby excluded as to product performance results, the accuracy of these data including any warranty of merchantability or fitness for any purpose. 013833

